Report Documentation Page				Form Approved OMB No. 0704-0188		
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.						
1. REPORT DATE 07 NOV 2007		2. REPORT TYPE		3. DATES COVE	RED	
	nterface at Li/Li+ I	on Conducting	5a. CONTRACT NUMBER FA520906P0156			
Channel (Suppleme			5b. GRANT NUMBER			
				5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Munichandraiah Nookala				5d. PROJECT NUMBER		
				5e. TASK NUMBER		
				5f. WORK UNIT NUMBER		
7. PERFORMING ORGANI Indian Institute of Chemistry,Bangalo	t of Inorganic and P	Physical	8. PERFORMING ORGANIZATION REPORT NUMBER N/A			
9. SPONSORING/MONITO	AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)			
		11. SPONSOR/MONITOR'S REPORT NUMBER(S)				
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.						
13. SUPPLEMENTARY NOTES						
dipthalocyanine (L sputtered SS, coppo obtained with SS el with gold electrode of impedance were chemical reactivity	i2Pc). Several symner, nickel and lithiu lectrodes consisted of produced a single obtained by varyin	ne effect of substrate netrical cells were as m electrodes. It was of two semicircles w semicircle with resi g the substrate mate rates used in the stu	ssembled using st found that the N ith total resistanc stance of 450 kOl erials. It was cond	ainless steel (yquist imped e of 1700 kO hm. Similarly	SS), gold foil, gold lance spectrum hm. But the cell v, different values	
15. SUBJECT TERMS						
16. SECURITY CLASSIFIC		17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON		
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified		3		

054090 Electrochemical Investigations of the Interface at Li/Li+ Ion Conducting Channel (Supplemental)
Munichandraiah Nookala, Indian Institute of Science

REPORT

For carrying out the experimental studies pertaining to the contract research titled "Electrochemical investigations of the interface at Li/Li⁺ ion conducting channel", EG&G PARC impedance analyzer, EG&G PARC potentiostat/galvanostat and Eco Chemie Autolab electrochemical systems have been under use. These equipment are 5-10 years old, and the data had been collected using out-dated computers. The purpose of requesting for additional funding of \$10000 was to replace the old computers with the latest models and to enhance the data acquisition capability. All old computers are now replaced with new computers. A part of this funds was also used for buying chemicals, cell hardware and fabrication charges.

Subsequent to replacement of old computers, the equipment are functioning satisfactorily and the data acquisition has become fast. Using these up-graded equipment, studies were undertaken to examine the effect of substrate materials on impedance behaviour of lithium dipthalocyanine (Li₂Pc). Several symmetrical cells were assembled using stainless steel (SS), gold foil, gold sputtered SS, copper, nickel and lithium electrodes. It was found that the Nyquist impedance spectrum obtained with SS electrodes consisted of two semicircles with total resistance of 1700 kOhm. But the cell with gold electrodes produced a single semicircle with resistance of 450 kOhm. Similarly, different values of impedance were obtained by varying the substrate materials. It was concluded that Li2Pc exhibits chemical reactivity with metallic substrates used in the study.